

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:


Listing of Claims:

1. (Currently Amended) A method for producing reversibly crosslinked cellulose ethers having lump-free stirrability and solvation delay on stirring into aqueous solutions containing said reversibly crosslinked cellulose ether as a sole viscosity developer, in which cellulose ethers having free OH groups are ~~first~~ admixed in water or in an organic suspension medium at a temperature in the range from 0 to 40 °C with chemical compounds containing at least one aldehyde group and at least one acid group, and in which the acid groups and aldehyde groups of the chemical compounds are then reacted with the OH groups of the cellulose ethers to form an ester bond or hemiacetal bond, the cellulose ether not being dissolved in the water or the suspension medium;

wherein the amount of chemical compound containing at least one aldehyde group and at least one acid group is in the range from 0.01 to 0.1 mol per mole of cellulose ether and

the solvation delay, providing an open time upon stirring said reversibly crosslinked cellulose ether into said aqueous solution, ~~ranges from~~ is a minimum of a few seconds ~~up to a plurality of hours,~~

and the chemical compound having at least one acid group and at least one aldehyde group is a compound of the general chemical formula



where X is a divalent alkylene group which has from 1 to 6 carbon atoms and can be saturated and straight-chain or branched, or a divalent saturated cyclo- or bicycloalkylene group having from 3 to 10 carbon atoms, or a divalent arylene group having from 6 to 10 carbon atoms, where these groups can further bear one or more substituents R which, in addition to hydrogen,

can also be alkyl radicals having up to 4 carbon atoms, alkoxy radicals having up to 4 carbon atoms, OH groups, halogens, nitro groups, nitrile groups or mixtures thereof, and where y can be either 0, 1 or 2.

2. (Canceled)

3. (Canceled) Please cancel Claim 3.

4. (Previously Presented) The method as claimed in claim 1, wherein the chemical compound having at least one acid group and at least one aldehyde group is glyoxylic acid.

5. (Canceled)

6. (Previously Presented) The method as claimed in claim 1, wherein the cellulose ethers having free OH groups are selected from methylcellulose, ethylcellulose, carboxymethylcellulose, hydroxyethylcellulose, hydroxypropylcellulose, methylhydroxyethylcellulose, methylhydroxypropylcellulose or ethylhydroxyethylcellulose.

7. (Previously Presented) The method as claimed in claim 1, wherein the cellulose ethers are admixed with the compound containing at least one aldehyde group and at least one acid group over a time period in the range of from 10 to 60 min.

8. (Previously Presented) The method as claimed in claim 1, wherein the acid groups and the aldehyde groups are reacted with the OH groups of the cellulose ethers at a temperature in the range from 50 to 150 °C over a time period in the range of from 1 to 120 min.

9. (Previously Presented) The method as claimed in claim 1, wherein the cellulose ethers are first admixed in organic suspension media selected from acetone, lower alcohols having from 1 to 4 carbon atoms, diethyl ether, ethers having alkyl chains having up to 8 carbon atoms per

chain, cyclic ethers, ethylene glycol dimethyl ether, diethylene glycol dimethyl ether, triethylene glycol dimethyl ether, tetraethylene glycol dimethyl ether, straight-chain and branched hydrocarbons having up to 12 carbon atoms, cyclic hydrocarbon compounds, or aromatic hydrocarbon compounds.

10. (Canceled)

11. (Currently Amended) A method as claimed in Claim 1, wherein the cellulose ether is pre-moistened with 40 to 80 % water, based on the amount of cellulose ether, or pre-suspended in 30 to 60% organic suspension medium, based on the amount of cellulose ether prior to admixing.

12. (Previously Presented) A method as claimed in Claim 1, wherein the chemical compounds containing at least one aldehyde group and at least one acid group are not released upon dissolving said reversibly crosslinked cellulose ether in a neutral or weakly acidic aqueous solution.

13. (Canceled) Please cancel Claim 13.

14. (Currently Amended) A method for producing reversibly crosslinked cellulose ethers having lump-free stirrability and solvation on stirring into aqueous solutions comprising pre-moistening cellulose ether having free OH groups with 40 to 80 % water, based on the amount of cellulose ether,

initially admixing a the pre-moistened cellulose ether composition comprising cellulose ethers having free OH groups in with water at a temperature in the range from 0 to 40 °C with and chemical compounds containing at least one aldehyde group and at least one acid group, the cellulose ether not being dissolved in the water or the suspension medium;

comminuting said admixed cellulose ether composition;

milling the comminuted cellulose ether composition; and

drying the milled cellulose ether composition to react the acid groups and aldehyde groups of the chemical compounds with the OH groups of the cellulose ethers to form an ester bond or hemiacetal bond.

15. (Currently Amended) A method for producing reversibly crosslinked cellulose ethers having lump-free stirrability and solvation on stirring into aqueous solutions comprising pre-suspending cellulose ether having free OH groups in 30 to 60% organic suspension medium, based on the amount of cellulose ether,

~~initially admixing a cellulose ether composition comprising the pre-suspended~~ cellulose ether[[s]] having free OH groups ~~in~~ with an organic suspension medium at a temperature in the range from 0 to 40 °C ~~with~~ and chemical compounds containing at least one aldehyde group and at least one acid group, the cellulose ether not being dissolved in ~~the water or~~ the suspension medium;

filtering the admixed cellulose ether composition

drying the filtered cellulose ether composition;

comminuting the filtered cellulose ether composition; and

heating the comminuted cellulose ether composition to react the acid groups and aldehyde groups of the chemical compounds with the OH groups of the cellulose ethers to form an ester bond or hemiacetal bond at a temperature ranging from 50 to 105 °C.